

AMBLYGON TA 15-2

Special grease for long-term lubrication and high temperatures



Your benefits at a glance

- Versatile grease for many applications subject to high loads
- Long service life even when exposed to high temperatures or aggressive media
- Long service life due to the high resistance to water and water vapour
- Long service life due to the excellent adhesion to the friction points
- Improved sealing effect due to high adhesion
- Low maintenance due to good corrosion protection

Your requirements - our solution

AMBLYGON TA 15/2 is a long-term and high-temperature lubricating grease based on mineral oil and polyurea. This lubricating grease is used for long-term or lifetime lubrication in the machine-building sector covering a wide service temperature range up to 150 °C. AMBLYGON TA 15/2 offers good adhesion, resistance to hot and cold water and diluted alkaline and acid solutions. AMBLYGON TA 15/2 is resistant to oxidation and ageing and protects against corrosion.

Application

AMBLYGON TA 15/2 lubricates bearings and joints subject to high temperatures and loads, for example in

- conveyors
- kilns (rotary tubular kilns)
- water pumps
- hot rollers
- tarmac laying machines

- gate valves
- seals
- washing machines and dishwashers
- impact mechanism in power tools
- joints, hinges
- king pins

AMBLYGON TA 15/2 is also used in combination with mineral-oil-resistant elastomer seals.

Application notes

Prior to series application we recommend checking compatibility with elastomers, if possible in the component under conditions similar to actual use.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	AMBLYGON TA 15/2
Cartridge 400 g	+
Can 1 kg	+
Bucket 25 kg	+
Bucket 50 kg	+
Drum 180 kg	+

AMBLYGON TA 15-2

Special grease for long-term lubrication and high temperatures



Characteristics	AMBLYGON TA 15/2
Article number	020109
Composition, thickener	polyurea
Composition, type of oil	mineral oil
Service temperature, lower limit	-20 °C
Service temperature, upper limit	150 °C
Density, Klüber method: PN 024, 20°C	approx. 0.93 g/cm ³
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	285 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	315 0.1 mm
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approx. 18 mm ² /s
Kinematic viscosity of the base oil, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approx. 220 mm ² /s
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 168 h	≤ 1 corrosion degree
Oil separation, DIN 51817 N, 168 h, 40°C	≤ 5 % by weight
Flow pressure, DIN 51805-2, -20°C	≤ 1400 mbar
Dropping point, DIN ISO 2176 / IP 396	≥ 220 °C
Speed factor (n x dm)	approx. 350000 mm/min
Water resistance, DIN 51807-1, 3 h, 90°C	0 - 90 rating
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx. 60 months	

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 95 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.