

Klüberpaste HEL 46-450

High-temperature screw paste



Your benefits at a glance

- Reliable screw connection ensured by constant and sufficient preload force
- Easy release also after long time at high temperature
- Approved in Ford tox. No. 138624

Your requirements - our solution

Klüberpaste HEL 46-450 is a black hot screw paste for high-alloy steels. It contains fully synthetic polyalkylene glycol and ester base oils and a combination of inorganic solid lubricants.

Klüberpaste HEL 46-450 is suitable for a temperature range between -40 °C and 1000 °C. In the normal temperature range (i.e. below 200 °C) it shows good anticorrosion behaviour and good water resistance. Above 200 °C it acts as a dry lubricant.

Application

Screw paste for conventional and high-alloy steels (Cr-Ni steels) up to 1000 °C.

Lubricating and assembly paste for connections in hot air ducts (e.g. automotive exhaust systems). For connecting elements in turbochargers and compressors.

Application notes

It is important to clean and degrease the contact surfaces thoroughly before applying Klüberpaste HEL 46-450.

A thin layer of paste is then applied by brush, leather cloth or plastic sponge.

Klüberpaste HEL 46-450 spreads easily over the entire surface and thus prevents excess lubrication.

Close container immediately after use in order to prevent contamination.

The friction values indicated on page 2 in the Section Product Data were determined with two different materials. Other materials/surfaces have to be checked accordingly.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberpaste HEL 46-450
Can 750 g	+
Bucket 30 kg	+
Drum 180 kg	+
Characteristics	Klüberpaste HEL 46-450
Article number	089032
Colour space	black
Service temperature, lower limit	-40 °C
Service temperature, upper limit	1000 °C

Klüberpaste HEL 46-450

High-temperature screw paste



Characteristics	Klüberpaste HEL 46-450
Density, Klüber method: PN 024, 20°C	approx. 1.43 g/cm ³
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	325 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	340 0.1 mm
SKF-EMCOR, DIN 51802, Klüber method: distilled water, 168 h	≤ 1 corrosion degree
Flow pressure, DIN 51805-2, -35°C	≤ 600 mbar
Dropping point, DIN ISO 2176 / IP 396	≥ 250 °C
Four-ball tester, welding load, DIN 51350-4	≥ 5000 N
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, averaged bearing surface friction coefficient (initial tightening), external test	0.11
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, averaged thread friction coefficient (initial tightening), external test	0.09
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, standard deviation (S) of averaged bearing surface friction coefficient (initial tightening), external test	0.015
Friction coefficient screw test, hexagon bolts M10 x 30-8.8, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, nut M10-8, plain and degreased, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 50 Nm, standard deviation (S) of averaged thread friction coefficient (initial tightening), external test	0.01
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, averaged bearing surface friction coefficient (initial tightening), external test	0.09
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, averaged thread friction coefficient (initial tightening), external test	0.12
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, standard deviation (S) of averaged bearing surface friction coefficient (initial tightening), external test	0.006
Friction coefficient screw test, hexagon bolts M10 x 50-A2-70, DIN EN ISO 4017, tightening speed $n = 5 \text{ min}^{-1}$, number of screws = 20, material of the nut A2, face material 42CrMo4 with roughness Ra 1.6, tightening torque MA = 40 Nm, standard deviation (S) of averaged thread friction coefficient (initial tightening), external test	0.03
Water resistance, DIN 51807-1, 3 h, 90°C	≤ 1 - 90 rating
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüberpaste HEL 46-450

High-temperature screw paste



Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 95 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.