

WOLFRASYN ULAF

Graphite containing high-temperature paste



Your benefits at a glance

- For the thin-film lubrication of low-speed rolling and plain bearings
- For lubricant applications up to 400 °C
- Also suitable for low temperatures
- High load-carrying capacity

Your requirements - our solution

WOLFRASYN ULAF is a graphite-containing high-temperature paste for thin-film lubrication of rolling and plain bearings. It has a chemical composition of polyalkylene glycol oil and an inorganic solid lubricant (graphite). The synthetic base oil evaporates at temperatures above 200 °C. The solid lubricant residue is effective up to 400 °C as a dry lubricant.

Application

WOLFRASYN ULAF has proven effective as a lubricant for kiln cart bearings in the ceramic industry and for feeder bearings subject to high temperatures in the glass industry. Other possible applications: as a bearing lubricant for roller tables in steel plants, for conveyor and transport chains in high-temperature applications and as a lubricant for plain bearings operating at high temperatures.

Application notes

NOTE:

Always apply WOLFRASYN ULAF in a thin layer! Clean the friction point with a sol-vent and remove any corrosion agent in the bearing before applying WOLFRASYN ULAF. Then use a brush of medium hardness to apply an even layer of WOLFRASYN ULAF to the entire raceway of the bearing. We recommend rotating the bearing components several times while applying the lubricant in order to ensure an even distribution over the raceway. If, during the rotation, a grease collar appears, remove it with the brush. Approximate values for greasing:

Polished metal bearings should be filled to a maximum of 15 % of the free bearing space. The filling quantity can be roughly calculated with the following equation:

$$d \times B \times 0.005 = g.$$

- d = diameter of the bearing bore in mm
- B = width of bearing in mm
- g = quantity of lubricant in g

In the case of phosphated bearings check if they are already lubricated. If this is the case, we recommend removing the lubricant before applying WOLFRASYN ULAF. The filling quantity is 10 % of the free bearing space.

At temperatures above 200 °C lubrication is effected by a dry lubricant film which is gradually used up. It should therefore be checked after approx. 12 months.

Relubrication with WOLFRASYN ULAF should generally take place after 24 months. The same is valid for dragging or squeaking bearings. Before relubrication blow the bearing carefully with dry air to avoid that any humidity precipitates. Shiny traces on the raceway indicate that the lubricant layer has been used up. In this case we generally recommend relubrication with WOLFRASYN ULAF. Bearings which were relubricated twice or which show wear marks or corrosion spots should be replaced.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes

Can 600 g

WOLFRASYN ULAF

+

WOLFRASYN ULAF

Graphite containing high-temperature paste



Characteristics	WOLFRASYN ULAF
Article number	003001
Colour space	black
Service temperature, lower limit	-30 °C
Service temperature, upper limit	400 °C
Density, Klüber method: PN 024, 20°C	approx. 1.3 g/cm ³
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, lower limit	290 0.1 mm
Worked penetration, DIN ISO 2137 / ASTM D217, 25°C, upper limit	320 0.1 mm
Flow pressure, DIN 51805-2, -30°C	≤ 1400 mbar
Four-ball tester, welding load, DIN 51350-4	≥ 3600 N
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx. 36 months	

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 95 years.

Klüber Lubrication München GmbH & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München GmbH & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München GmbH & Co. KG and if source is indicated and voucher copy is forwarded.