

perma BIO SYN 100 (S064)

Previous name: perma Bio oil, low viscosity S064

RAPIDLY BIODEGRADABLE MULTI-PURPOSE OIL

perma BIO SYN 100 (S064) is a fully synthetic multi-purpose oil which fall under water hazard class 1, i.e. it is not hazardous to water. It has an excellent viscosity-temperature relation and a wide service temperature range. perma BIO SYN 100 (S064) protect against corrosion and wear and it is very adhesive and resistant to ageing and oxidation. In the FZG test, DIN 51354 pt 2 (A/8.3/90) this oil has a scuffing load stage ≥ 12 and meet the CLP requirements. In accordance with CEC-L-33-A-94, biodegradability after 21 days is $> 70\%$.

Advantages



MULTI-PURPOSE OIL



RAPIDLY BIODEGRADABLE



WATER HAZARD CLASS 1



EXCELLENT VISCOSITY-TEMPERATURE RELATION



GOOD ANTIWEAR BEHAVIOR



VERY ADHESIVE

Application

perma BIO SYN 100 (S064) is used for the lubrication of open drive and conveyor chains, spindles and joints as well as for spur, bevel and worm gears and pertinent machine elements, such as couplings, plain and rolling bearings. perma BIO SYN 100 (S064) is used in agricultural and forestry equipment, water treatment installations, gardening equipment. perma BIO SYN 100 (S064) is especially suitable for applications where oil leakage might contaminate the environment.

APPLICATION INFORMATION

perma BIO SYN 100 (S064) is a lubricant especially developed for perma lubrication systems. To ensure adequate metering and maintenance-free lubrication, this product is only available in perma lubrication system. Depending on temperature and exposure time, synthetic lubricants on an ester base may have an impact on the functional capacity of rubber-elastic sealing materials. Seals made of NBR materials can be used at permanent temperatures up to max. 80 °C. For higher temperatures we recommend to use seals made of FKM materials. Paints may be attacked by synthetic lubricants. When applying perma BIO SYN 100 (S064) we recommend the use of two-component paints for interior coating.

SHELF LIFE

Shelf life is approx. 12 months if the product is stored in its unopened original container in a dry and frost-protected place.

PACKAGING

- perma lubrication systems
- Bottle 1 ltr
- Bottle 5 ltr

Product data

Base oil	Ester
ISO VG DIN 51519	100
Kinematic viscosity, DIN 51561, at 40 °C, mm ² /s at 100 °C, mm ² /s	100 15
Colour	Orange
Density, DIN 51757, at 20 °C, g/cm ³ , approx.	0.94
Viscosity index, DIN ISO 2909	> 140
Pourpoint, DIN ISO 3016, °C.	< -30
Service temperature range, °C	- 30 to 110
Elastomer compatibility towards 72 NBR 902 at 100 °C / 168 h change in volume % change in hardness (Shore A), approx.	< +15 -6



Gears



Sliding bearings



Spindles



Chains